



FLAX LOW TWIST ROVING TEX 2000

Technical Datasheet

SPECIFICATIONS

GENERAL PARAMETERS

| | | | | |
|-----------------|------------|-------------|---------------|-------------------------|
| LINEAR DENSITY: | TEX | 2000 | COLOR: | NATURAL |
| | Nm | 0,5 | FLAX CONTENT: | 100% |
| TORSION: | tpm | 20 | FLAX ORIGIN: | EU non-EU |

FIBER TREATMENTS

| | | | |
|------------|------------------------------|-------------------------------|----------------|
| WASHING: | <input type="checkbox"/> YES | <input type="checkbox"/> NONE | Alkali washing |
| BLEACHING: | <input type="checkbox"/> YES | <input type="checkbox"/> NONE | |
| SIZING: | <input type="checkbox"/> YES | <input type="checkbox"/> NONE | |
| ADDITIVES: | <input type="checkbox"/> YES | <input type="checkbox"/> NONE | |
| OTHER: | <input type="checkbox"/> YES | <input type="checkbox"/> NONE | |

STANDARD BOBBIN CONDITIONING

| | |
|-----------|---------------------------|
| CORE: | INTERNAL UNWINDING |
| TYPE: | CYLINDRIC |
| WEIGHT: | 1.5 kg |
| DIAMETER: | 135 mm |
| HEIGHT: | 140 mm |
| LENGTH: | ~750 m |
| HUMIDITY: | ~9 % |

STORAGE

Recommended low humidity storage (< 50% R.H.); limited exposure to sunlight

DRY FLAX ROVING PARAMETERS

| BREAKING STRENGTH | TENACITY | CV BREAKING | ELONGATION | RKM | RKM | RKM | RKM | Um |
|-------------------|----------|--------------|------------|-----|---------------|------|--------|------|
| (N) | (cN/TEX) | STRENGTH (%) | (%) | min | 3 points mini | max | medium | (%) |
| 295,0 | 14,80 | 19,5 | 1,9 | 7,8 | 8,9 | 21,1 | 15,2 | 18,5 |

| CVm | Points g | Points g | Points g | Points g | Points g | Points g | Points g | Points g |
|------|----------|----------|----------|----------|----------|----------|----------|----------|
| (%) | (-40%) | (-50%) | (+35%) | (+50%) | (+70%) | (+100%) | (+200%) | (+400%) |
| 22,7 | 4008,8 | 1428,8 | 1067,6 | 293,6 | 42,8 | 2,4 | 330,8 | 15,2 |

data obtained according to Uster specification for natural fibers

| PARAMETERS | UNITS | VALUES |
|------------------------|-------------------|--------|
| TENSILE STRENGTH | MPa | 212 |
| TENSILE MODULUS | GPa | 12.0 |
| TENSILE ELONGATION | % | 1.9 |
| DENSITY OF FLAX FIBERS | g/cm ³ | 1.44 |



FLAX LOW TWIST ROVING TEX 1000

Technical Datasheet

COMPOSITE PARAMETERS

MECHANICAL PROPERTIES OF MATRIX

| PARAMETERS | UNITS | VALUES |
|---------------|-------|-----------|
| TYPE OF RESIN | | EPOXY |
| STRENGTH | MPa | 70 |
| MODULUS | GPa | 2 < E < 3 |
| STRAIN | % | > 4 |

MANUFACTURING PROCESS

THERMOCOMPRESSION

BASED ON ISO 10618:2004 (ADAPTED TO NATURAL FIBERS)

MECHANICAL PROPERTIES OF COMPOSITE*

*tensile tests performed according to standard ISO 527

| TYPE OF VALUES | | EXPERIMENTAL Vf=57% | NORMALIZED ³ Vf=50% |
|---------------------------------|-------|------------------------|-----------------------------------|
| PARAMETERS | UNITS | VALUES | |
| TENSILE STRENGTH | MPa | 388 | 347 |
| TENSILE MODULUS E1 ¹ | GPa | 38.7 | 34.4 |
| TENSILE MODULUS E2 ² | GPa | 28.7 | 25.4 |
| TENSILE ELONGATION | % | 1.3 | 1.3 |

¹ E1 - strain (%) between 0,0005 and 0,001

² E2 - strain (%) between 0,003 and 0,005

³ Experimental results recalculated to given fiber volume fraction Vf

PERFORMANCE OF FLAX FIBER IN COMPOSITE (BACKCALCULATED)*

*according to CELC guidelines

| PARAMETERS | UNITS | VALUES |
|---------------------------------|-----------------------------|--------|
| FIBER STRENGTH | MPa | 658 |
| TENSILE MODULUS E1 ¹ | GPa | 68.3 |
| TENSILE MODULUS E2 ² | MPa | 50.6 |
| SPECIFIC STRENGTH | $\frac{MPa}{g \times cm^3}$ | 457 |
| SPECIFIC STIFFNESS | $\frac{GPa}{g \times cm^3}$ | 47 |

¹ E1 - strain (%) between 0,0005 and 0,001

² E2 - strain (%) between 0,003 and 0,005

PROCESSING GUIDELINES

1. Flax roving is compatible with epoxy and polyester resins.
2. Flax reinforcement can be used directly however to obtain the highest performance in composite it is recommended to dry fibers prior to impregnation (110°C / 15min or 60°C / 4h).
3. For textile manufacturing (weaving, knitting etc.) it is important to respect the requirements for natural fiber processing (air relative humidity ~64%, temperature ~22°C).

For further details please contact us on: www.safilin.fr